

Technical Data

ISO 9001 & 50 001 certified QMS

The carbon footprint of this grade is : 561 in g eq CO₂/m² (Scopes 1+2+3)

This grade is made with 100% recycled fibres and is guaranteed 100% recyclable (norm EN 13430).

Papers complying with the regulation Bfr XXXVI.

Item designation DD CB 301					Cylinder thickness		Number of flutes/m
Caliper (+/- 5% / ISO3034) :					C	3,6	126
Weight (+/- 7% /ISO536) :					B	2,7	154

Papers Composition

Inner liner	Fluting 1	Centre liner 1	Fluting 2	Centre liner 2	Fluting 2	Outer liner
TL135	CAN085	CAN085	CAN085			TL135

Technical characteristics

Theoretical values

Tests	FCT (kN/100 can / m) (Flat crush test)	Burst (kPa)	ECT (kN/m) (Edge crush test) 10 % loss of t hickness = ECT : -25%	BCT (daN) (Theorical Box Crush Test)	Regular Slotted Case FEFCO 201
	ISO 3035	ISO 2759	ISO 3037		L=400 mm
Average	Impossible	914	7,18	488	l=300 mm
Min	Impossible	868	6,46	440	h=300 mm

Averages figures for 95% of the measured values. All tests are carried out under conditions of 23°C and 50% RH. ISO 187

All papers used are subject to strict quality controls.

Edited : 10/06/2022