

Technical Data

Mechanical properties

| | Standard | Unit | Value | | | | | |
|--|------------------------|-------------------|--------|------------|------------|------------|------------|------------|
| | | | M | D | ES | H | WA | |
| Apparent density* | DIN EN ISO 1183 | g/cm ³ | ~ 1.43 | ~ 1.43 | ~ 1.43 | ~ 1.43 | ~ 1.43 | |
| Yield stress (tensile strength) | DIN EN ISO 527 | MPa | > 45 | ≥ 50 | ≥ 48 | ≥ 45 | ≥ 55 | |
| Elongation at tear | DIN EN ISO 527 | % | > 20 | ≥ 15 | ≥ 20 | ≥ 20 | ≥ 15 | |
| Flexural strength | DIN EN ISO 178 | MPa | ≥ 80 | ≥ 75 | ≥ 75 | ≥ 70 | ≥ 80 | |
| Compressive strength | DIN EN ISO 844 | MPa | ≥ 70 | ≥ 65 | ≥ 65 | ≥ 60 | ≥ 70 | |
| Modulus of elasticity | DIN EN ISO 527 2/1A/50 | MPa | > 2500 | ≥ 2500 | ≥ 2500 | ≥ 2500 | ≥ 3000 | |
| Notched impact strength | DIN EN ISO 179-1ePA | KJ/m ² | ≥ 4 | ≥ 6 | ≥ 6 | ≥ 8 | ≥ 4 | |
| Impact strength | DIN EN ISO 179 | KJ/m ² | | | | | | |
| | | | 0 °C | no failure | no failure | no failure | no failure | no failure |
| | | | -20 °C | | no failure | no failure | no failure | |
| | | | -30 °C | | | no failure | no failure | |
| | | | -40 °C | | | | no failure | |
| Ball indentation hardness (358 N/30 s) | DIN EN ISO 2039 | MPa | ~ 100 | ~ 90 | ~ 90 | ~ 90 | ~ 100 | |

Thermal properties

| | Standard | Unit | Value | | | | |
|---|------------------------------------|-------|-------|------|------|------|------|
| | | | M | D | ES | H | WA |
| Vicat softening temperature | DIN EN ISO 306 (process B50) | °C | ≥ 75 | ≥ 72 | ≥ 72 | ≥ 72 | ≥ 75 |
| Deflection temperature | DIN EN ISO 75 | °C | ~ 68 | ~ 66 | ~ 66 | ~ 66 | ~ 68 |
| Coefficient of linear thermal expansion from -30 °C to +50 °C | DIN EN ISO 11359-2 (process Ae) | mm/mK | 0.08 | 0.08 | 0.08 | 0.08 | 0.08 |
| Thermal conductivity from 0 °C to +60 °C | DIN EN ISO 22007 | W/mK | 0.16 | 0.16 | 0.16 | 0.16 | 0.16 |

Fire rating

B S3 D0 - CE Approved
C S3 D0

MaterialSolutions

www.materialsolutions.ie

+ 3 5 3 1 4 0 9 8 0 0 0

sales@materialsolutions.ie