

PRODUCT DATA SHEET

SP 3523 Opaque Matt

Issued: 03/2022

Introduction

Avery Dennison SP 3523 Opaque Film is a matt white, self-adhesive polyolefin, with grey permanent adhesive for overposting needs, optimized for short-term promotional graphics.

It allows for more sustainable digital printing compared to standard vinyl options due to its nature of being PVC-free and thus containing no chlorine, phthalates and other halogens, reducing the emissions of volatile organic components (VOC's). The product is also featuring a solvent-free adhesive.

Conversion

SP 3523 Opaque Film is suitable for UV-curing and latex inks. To achieve the best possible print quality, please make sure the correct ICC Profile and printer settings are used.

Recommendations

- » Interior & exterior signs
- » Temporary promotional and point of sale advertising and all applications to flat or regular surfaces where additional opacity may be required

Features

- » PVC-free face film and solvent-free adhesive
- » Attractive white appearance
- » Excellent printability and handling on selected printers
- » Easy cutting and application on a wide variety of substrates
- » Good opacity by using grey adhesive system, improving overposting possibilities



Face Film

90 micron matt white polyolefin film



Adhesive

Permanent, grey, acrylic based solvent-free adhesive



Backing

Clay coated kraft paper, 125 g/m2



Durability

3 years (vertical, unprinted)



Shelf Life

2 years

Physical Characteristics

	Test method ¹	Results
Product		
Caliper, facefilm (micron)	ISO 534	90
Caliper, facefilm + adhesive (micron)	ISO 534	116
Fire Classification	EN13501-1	B-s1,d0
Dimensional stability (mm max.)	FINAT FTM 14	0.4
Shelf life (years)	Stored at 22° C/50-55 % RH	2
Durability ² (years)	Vertical exposure	3
Adhesive		
Adhesion, initial (N/m)	FINAT FTM-1, stainless steel	240
Adhesion, after 24 hours (N/m)	FINAT FTM-1, stainless steel	350
Temperature range		
Application temperature (Minimum °C)		10
Service temperature (°C to +°C)		-40 to +80
Chemical properties³		
Chemical resistance	Mild acids	No effect
Solvent resistance	Mild alkalis	No effect
Solvent resistance	Applied to aluminium	No effect exposed to: oils, greases, aliphatic solvents, motor oils, heptane, kerosene and JP-4 fuel.

Important

Information on physical and chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use.

All technical data are subject to change. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.

1) Test methods: More information about our test methods can be found on our website.

2) Durability: The durability is based on middle European exposure conditions. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing south; in areas of long high temperature exposure such as southern European countries; in industrially polluted areas or high altitudes, exterior performance will be decreased..

3) Prolonged immersion in gasoline and similar fluids is not recommended.

Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>.

Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.

© 2022 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.