

Issue 8. July 2015

FILTAflo® ANTI-DUST FILTRATION TAPE

ADT10, ADT16, ADT20, ADT25, ADT30, ADT40, ADT50, ADT60

RA1700 Series

Product patented: European Patent No. 0920899 (23.11.98)

TECHNICAL DETAILS	TYPICAL VALUE	UNITS
Carrier	Blue / Grey spunbound synthetic fibre	
Thickness (total)	0.51	mm
Edana 30.4-89		
Weight	70	gsm
Edana 40.3-90		
Adhesive type	Thermoplastic Rubber Resin with UV inhibitor	
Liner (s.sided Amber)	80	gsm
Peel adhesion	1200	N/m
Tack	1600	N/m
Tensile strength MD	2500	N/m
Tensile strength CD	1980	N/m
Edana 20.2-89		
Elongation MD	>80	%
Elongation CD	>90	%
Edana 20.2-89		
Tear strength MD (fabric only) CD	57 / 74	N
Edana 70.2-89		
Air permeability	140	mm ³ /mm ² /min
Edana 140.1-81		
Water repellancy	135	mm/H ₂ O
Edana 120.1-80		
Abrasion	>100	Rubs /1,5kg
Recommended application temp range:	5 to 25	°C
Service temperature range	-20 to + 80	°C
Shelf Life: (under normal storage conditions)	12 months (minimum)	

contd...

FILTAflo ANTI-DUST FILTRATION TAPE

contd...

Particle Test Retention

Test area	100	cm ²
Test flow	15	litres / min.
Face velocity	2.5	cm / sec.
Material pressure drop	5	Pa
Barometric pressure	1002	mbar
Temperature	20	°C
Humidity	50	% RH
Efficiency under above conditions	22%	Retained particles

Class acceptance within standards EN 779 and BS 4400

(Tests carried out using Challenge aerosol NaCl poly dispersed particle size 0.02 to 1.1 micrometres. Mass median 0.6 micrometres measuring longest diagonal, or 0.4 micrometres measured aerodynamically.)

N.B. Edana test methods: EDANA: European Disposables and Nonwovens Association

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY. ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR DETERMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.