

Properties	Method of Testing	Units	Value
Melt temperature		Deg C	160-165
Max. use temp.		Deg C	90
Vicat softening point	ISO 306/A	Deg C	152
HDT	ISO 75/B	Deg C	100
Flexural modulus	ISO/178	N/mm ²	1350
Tensile strength @ yield	ISO R 527	N/mm ²	27
Elongation @ yield	ISO R 527	%	8
Density	ISO 1183	G/cm ³	0.9
Izod impact strength 23 deg C -20 deg C	ISO 180	kJ/cm ²	40 8
Rockwell hardness	ISO 868	D scale	68

If you have any queries, please contact our customer service team at **+353 (1) 409 8000** who will be happy to advise you.