

FABRENE® V734W8W8

Made from high density polyethylene tapes, coated on both sides with low density polyethylene.
Contains a flame retardant additive.

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	g/m2		109.5	ASTM D3776
Warp Construction	Tapes/10cm	Warp	36	ASTM D3775
	Tapes/10cm	Weft	23	
Widths	mm		up to 3900	
Tensile Grab Strength	Newtons		Warp 520	ASTM D751
	Newtons		Weft 520	
Tear Strength * (tongue)	Newtons		Warp 290	ASTM D2261
	Newtons		Weft 290	
Coating	µm	White	23	ASTM D1777 MOD
	µm	White	23	
Flammability			PASS	NFPA 701-04 Method 2
Nominal Thickness	µm		145	ASTM D1777 MOD

* Includes force to shift tapes - Tear may be crosswise to direction of force.

Fabrene® V734W8W8 contains some ultraviolet inhibitors but is not recommended for extended outdoor exposure.
Rolls come on 6" cores. For further information, contact your FABRENE Inc. representative.

Suggested Applications: Billboards, Banners, Print Media

SALES INQUIRIES

Fabrene Inc.
Tel: (888) 322-7363 ext 234
Tel: (705) 476-7057 ext 234
Fax: (705) 476-7787

ORDER DESK

North Bay, ON, Canada
Tel: (888) FABRENE
(888) 322-7363
ext. 222 or 226
Fax: (705) 476-0665

MAILING ADDRESS

Fabrene Inc.
240 Dupont Rd.
P.O. Box 4040
North Bay, ON, Canada
P1B 9B4

Date: 2011/11/16

