

Mactac ColourWrap Series

PRODUCT DESCRIPTION

Mactac ColourWrap series are 3D conformable coloured cast wrapping films with gloss, gloss metallic, matt and matt metallic finishes coated with micro-structured acrylic adhesive.

Mactac ColourWrap Series has been developed especially for full vehicle wrapping purposes.

Face material

80µm gloss, matt and metallic **3D conformable cast vinyl**

Adhesive:

Repositionable clear solvent based acrylic adhesive.

Liner

Highly stable 145 gsm white micro-embossed PE coated paper.

TYPICAL USE

Mactac ColourWrap Series has been developed for vehicle and boat* customisation enabling full wrapping around curves and recesses on painted metal substrates. (*above the waterline)

SHELF LIFE

2 years, when stored at 15-25°C and ± 50 % relative humidity

PHYSICAL PROPERTIES (TYPICAL VALUES)

Average values Test method

Adhesive data, 23°C (N/25 mm)

Peel 20 min on Stainless Steel	13	FTM1
Peel 24 hours on Stainless Steel	17	

Facefilm data, 23°C

Tensile Strength	> 25 MPa	DIN ISO 527-3
Elongation at break	>150%	DIN ISO 527-3

Dimensional stability

Shrinkage (48 hours at 70°C applied on aluminium)	Max. 0.3 mm	FTM 14
--	-------------	--------

Temperature ranges

Application temperature	+ 10°C to + 40°C
Service temperature range of use	- 40°C to + 90°C

EXPECTED DURABILITY

Vertical Durability			
	Zone 1	Zone 2	Zone 3
White & Black	8 years	5 years	3 years
Colours*	6 years	4 years	2 years
Metallics	4 years	3 years	1.5 years
Horizontal Durability			
White & Black	5 years	3 years	1.5 years
Colours*	3 years	2.5 years	1 year
Metallics	2 years	1.5 years	6 months

*Note: Despite being solid colours, the expected durability of Gloss Saffron Yellow (LA0660001), Gloss Lemon Yellow (BQ7980001), Gloss Yellow (LA0870001) and Gloss Frog Green (LA0740001) is equal to the one of metallics (row 3 in the table).

This information is based on artificial aging according to ISO 4892-3.

Exterior boat application with Mactac Sealer: above data reduced by 30%

For more details about durability and zone classification, please refer to TB 7.5 "Outdoor Durability of Mactac Graphics - Self-adhesive films"

Exposure to severe temperatures, ultraviolet light, and/or conditions in Southern European countries, tropical, subtropical or desert regions will cause more rapid deterioration. This also applies to polluted areas, high altitude and south-facing exposure.

PROCESSING

Clean and degrease the substrate

All surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination. Use soap and water to remove the dust and degrease with Mactac Cleaner (Product Code: BO7680001). Application of the product is recommended only on painted metal surfaces. Painted metal surfaces selected for application need to be properly cured accordingly to paint manufacturer's instruction.

Application

Apply Mactac ColourWrap Series with the dry application method.

For full details on application of Mactac ColourWrap Series, please refer to Technical Bulletin 3.0.

Application on boat(above the waterline)

We recommend sealing the edges using Mactac Sealer (Product Code: BP2540001).

Removability

Once heated, Mactac ColourWrap series is easy to remove, leaving almost no adhesive residue on car body.

Some adhesive residue may be expected after film removal. Eventual adhesive residues can be removed with Mactac Remover (Product Code: BO7710001).

REMARKS

Compatibility with paints and lacquers should be tested by the end-user, prior to use.

Due to the finish and manufacturing process of

Mactac ColourWrap series, variances in colour can be observed when the material is oriented in different directions. While working with Mactac ColourWrap series, always keep the application direction of the film consistent with the orientation of the film. That is needed from the moment you cut from the roll and until it is applied to the vehicle.

Some slight colour shift may occur between rolls or lots, therefore, minimizing the mixing of rolls/lots on a specific vehicle is recommended.

DISCLAIMER

Important notice Information on physical and chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use. All technical data are subject to change. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.

Disclaimer and warranty Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>. Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.